



11

COLOURS

1

SIZE

1

FINISH

0

SPECIAL PIECES

Variations in colour and patterning create interplays of light which add vibrancy to spaces.

Lenton introduces a collection with a decidedly contemporary appeal and ultra-glossy, flawed surfaces in 11 shades.

COLOURS AVAILABLE




01



02



03



04



05



12



10



08



09



11



07

PORCELAIN

10mm Thick

Wall/Floor

Interior/ Exterior

Gloss

All Tiles

All Tiles

60x240mm

✓

Wall Only

Interior & Exterior

Group	Bla – Porcelain	Standard	Requirement	Established Values
Length & Width		ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness		ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness		ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness		ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity		ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption		ISO 10545-3	Eb ≤ 0.5 %	≤ 0.5 %
Breaking strength		ISO 10545-4	≥ 1300N	≥ 1300N
Modulus of rupture		ISO 10545-4	Ave Minimum 35 N/mm ²	Ave min 35 N/mm ²
Resistance to surface abrasion		ISO 10545-7	Declare Class	PEI 3
Thermal shock resistance		ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost Resistance		ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts		ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids		ISO 10545-13	Declare Value	GHA
Resistance to low concentrations of alkalis and acids		ISO 10545-13	Declare Value	GLA
Resistance to Stain		ISO 10545-14	Declare Value	Class 5
Reaction to Fire		-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.