



3

COLOURS

3

SIZES

1

FINISHES

1

SPECIAL PIECES

KASTE01 a porcelain concrete-effect tile and shower tray collection has been designed to effortlessly complement any modern interior. Suited to wet rooms due to its high slip resistance (rated PTV 36+) and coordinating KASTE01 shower tray which will give your wet room a seamless finish.


The tile range consists of 3 colours in 2 formats of 60x60cm & 90x90cm with 1 co-ordinating shower tray format option in 90x135cm.

## SIZE GUIDE


600x600mm



900x900mm



900x1350mm



## COLOURS AVAILABLE


Basalt



Grit



Cement





Dimensions	Multiple
Finish	Matt / Anti Slip
Body	Porcelain
Wall/Floor	Wall & Floor
Interior/ Exterior	Interior / Exterior
Group	BI <sub>a</sub>
Pendulum Dry (4S)	36+
Pendulum Wet (4S)	0-24
Pendulum Wet (TRL)	0-24

Available Sizes
600x600x10mm 900x900x10mm

	Standard	Requirement	Typical Test Value
Length & Width	ISO 10545-2	$\pm 0.6\% \leq 2\text{mm}$	Pass
Thickness	ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
Straightness	ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
Flatness	ISO 10545-2	$\pm 0.5\% \leq \pm 2.0\text{mm}$	Pass
Rectangularity	ISO 10545-2	$\pm 0.5\% \leq \pm 2.0\text{mm}$	Pass
Water Absorption	ISO 10545-3	$E_b \leq 0.5\%$	Pass
Breaking strength	ISO 10545-4	$\geq 1300\text{N}$	Pass
Modulus of rupture	ISO 10545-4	35 N/mm <sup>2</sup> Average min	Pass
Resistance to surface abrasion	ISO 10545-7	n/a	PEI 3
Frost Resistance	ISO 10545-12	Complies with Standard	Pass
Thermal Shock Resistance	ISO 10545-9	Complies with Standard	Pass
Resistance to Stain	ISO 10545-14	Min class 3	Pass
Resistance to chemicals	ISO 10545-14	Min Class B	Pass
Reaction to Fire	-	Floor/Wall class A1 FL/A1	Pass

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.